



US006811829B2

(12) **United States Patent**
Affinito et al.

(10) **Patent No.:** **US 6,811,829 B2**
(45) **Date of Patent:** **Nov. 2, 2004**

(54) **METHOD OF MAKING A COATING OF A
MICROTEXTURED SURFACE**

5,681,666 A 10/1997 Treger et al.
5,684,084 A 11/1997 Lewin et al.

(List continued on next page.)

(75) Inventors: **John D. Affinito**, Tucson, AZ (US);
Gordon L. Graff, West Richland, WA
(US); **Peter M. Martin**, Kennewick,
WA (US); **Mark E. Gross**, Pasco, WA
(US); **Paul E. Burrows**, Kennewick,
WA (US); **Linda S. Sapochak**,
Henderson, NV (US)

FOREIGN PATENT DOCUMENTS

(73) Assignee: **Battelle Memorial Institute**, Richland,
WA (US)

BE	704 297	2/1968
DE	9603746	4/1997
EP	0 299 753	1/1989
EP	0 340 935	11/1989
EP	0 390 540	10/1990
EP	0 547 550	6/1993
EP	0 590 467	4/1994
EP	0 722 787	7/1996
EP	0 787 826	7/1996
EP	0 916 394	5/1999
EP	0 931 850	7/1999
EP	0 977 469	2/2000
JP	6316316	6/1988
JP	64-18441	1/1989
JP	2-183230	7/1990
JP	08325713	12/1996
JP	09059763	3/1997
WO	WO 87 07848	12/1987
WO	WO 95 10117	4/1995
WO	WO 97 04885	2/1997

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 431 days.

(21) Appl. No.: **09/811,869**

(22) Filed: **Mar. 19, 2001**

(65) **Prior Publication Data**

US 2002/0102363 A1 Aug. 1, 2002

Related U.S. Application Data

(List continued on next page.)

(63) Continuation-in-part of application No. 09/212,780, filed on
Dec. 16, 1998, now Pat. No. 6,228,434.

(51) **Int. Cl.**⁷ **H05H 1/00**

(52) **U.S. Cl.** **427/488; 427/497; 427/509;**
427/398.1

(58) **Field of Search** **427/488, 497,**
427/509, 398.1, 506, 520, 562

OTHER PUBLICATIONS

Affinito, J.D., et al., "Vacuum Deposition of Polymer Elec-
trolytes on Flexible Substrates." "Proceedings of the Ninth
International Conference on Vacuum Web Coating." Nov.
1995 ed R. Bakish, Bakish Press 1995, p. 20-36.

Vossen, J.L., et al., Thin Film Processes. Academic Press,
1978. Part II, Chapter 11-1. Glow Discharge Sputter Depo-
sition.p. 12-63: Part IV, Chapter IV-I. Plasma Deposition of
Inorganic Compounds and Chapter IV-2 Glow Discharge
Polymerization.p. 335-397.

Penning, F.M., Electrical Discharges in Gasses, Gordon and
Breach Science Publishers. 1965. Chapters 5-6.p. 19-35.
and Chapter 8. p. 41-50.

Affinito, J.D., et al., "High Rate Vacuum Deposition of
Polymer Electrolytes," Journal Vacuum Science Technology
A 14(3). May/June. 1996, no page numbers.

(List continued on next page.)

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,475,307 A	10/1969	Knox et al.
3,607,365 A	9/1971	Lindlof
4,098,965 A	7/1978	Kinsman
4,283,482 A	8/1981	Hattori et al.
4,581,337 A	4/1986	Frey et al.
4,624,867 A	11/1986	Iijima et al.
4,695,618 A	9/1987	Mowrer
4,842,893 A	6/1989	Yializis et al.
4,954,371 A	9/1990	Yializis
5,032,461 A	7/1991	Shaw et al.
5,204,314 A	4/1993	Kirlin et al.
5,237,439 A	8/1993	Misono et al.
5,260,095 A	11/1993	Affinito
5,354,497 A	10/1994	Fukuchi et al.
5,395,644 A	3/1995	Affinito
5,427,638 A	6/1995	Goetz et al.
5,440,446 A	8/1995	Shaw et al.
5,536,323 A	7/1996	Kirlin et al.
5,547,508 A	8/1996	Affinito
5,554,220 A	9/1996	Forrest et al.
5,576,101 A	11/1996	Saitoh et al.
5,607,789 A	3/1997	Treger et al.
5,620,524 A	4/1997	Fan et al.
5,629,389 A	5/1997	Roitman et al.
5,652,192 A	7/1997	Matson et al.
5,654,084 A	8/1997	Egert
5,665,280 A	9/1997	Tropsha
5,681,615 A	10/1997	Affinito et al.

Primary Examiner—Bret Chen

(74) *Attorney, Agent, or Firm*—Dinsmore & Shohl LLP

(57) **ABSTRACT**

A method for conformally coating a microtextured surface.
The method includes flash evaporating a polymer precursor
forming an evaporate, passing the evaporate to a glow
discharge electrode creating a glow discharge polymer pre-
cursor plasma from the evaporate, cryocondensing the glow
discharge polymer precursor plasma on the microtextured
surface and crosslinking the glow discharge polymer pre-
cursor plasma thereon, wherein the crosslinking resulting
from radicals created in the glow discharge polymer precur-
sor plasma.

U.S. PATENT DOCUMENTS

5,686,360	A	11/1997	Harvey, III et al.	
5,693,956	A	12/1997	Shi et al.	
5,711,816	A	1/1998	Kirlin et al.	
5,725,909	A	3/1998	Shaw et al.	
5,731,661	A	3/1998	So et al.	
5,747,182	A	5/1998	Friend et al.	
5,757,126	A	5/1998	Harvey, III et al.	
5,759,329	A	6/1998	Krause et al.	
5,792,550	A	8/1998	Phillips et al.	
5,811,177	A	9/1998	Shi et al.	
5,811,183	A	9/1998	Shaw et al.	
5,821,692	A	10/1998	Rogers et al.	
5,844,363	A	12/1998	Gu et al.	
5,872,355	A	2/1999	Hueschen	
5,902,641	A	5/1999	Affinito et al.	
5,902,688	A	5/1999	Antoniadis et al.	
5,904,958	A	5/1999	Dick et al.	
5,912,069	A	6/1999	Yializis et al.	
5,919,328	A	7/1999	Tropsha et al.	
5,922,161	A	7/1999	Wu et al.	
5,945,174	A	8/1999	Shaw et al.	
5,948,552	A	9/1999	Antoniadis et al.	
5,955,161	A	9/1999	Tropsha	
5,965,907	A	10/1999	Huang et al.	
5,968,620	A	10/1999	Harvey et al.	
5,996,498	A	12/1999	Lewis	
6,013,337	A	1/2000	Knors	
6,045,864	A	4/2000	Lyons et al.	
6,083,628	A	7/2000	Yializis	
6,092,269	A	7/2000	Yializis et al.	
6,106,627	A	8/2000	Yializis	
6,146,225	A	11/2000	Sheats et al.	
6,165,566	A	12/2000	Tropsha	
6,207,239	B1	3/2001	Affinito	
6,214,422	B1	4/2001	Yializis	
6,217,947	B1	4/2001	Affinito	
6,224,948	B1 *	5/2001	Affinito	427/488
6,228,434	B1 *	5/2001	Affinito	427/488
6,228,436	B1	5/2001	Affinito	
6,231,939	B1	5/2001	Shaw et al.	
6,274,204	B1	8/2001	Affinito	
6,497,924	B2 *	12/2002	Affinito et al.	427/497
6,509,065	B2 *	1/2003	Affinito	427/488
6,544,600	B2	4/2003	Affinito et al.	
6,613,395	B2	9/2003	Affinito et al.	
6,627,267	B2	9/2003	Affinito	
6,656,537	B2 *	12/2003	Affinito et al.	427/488
2002/0125822	A1	9/2002	Graff et al.	
2003/0235648	A1	12/2003	Affinito et al.	

FOREIGN PATENT DOCUMENTS

WO	WO 97 22631	6/1997
WO	WO 98 10116	3/1998
WO	WO 98 18852	5/1998
WO	WO 99 16557	4/1999
WO	WO 99 16931	4/1999
WO	WO 00/36665	6/2000
WO	WO 01/81649	A1 11/2001
WO	WO 01/82336	A2 11/2001
WO	WO 01/82389	A1 11/2001
WO	WO 01/89006	A1 11/2001

OTHER PUBLICATIONS

Inoue et al., Fabrication of a Thin Film of MNA by Vapour Deposition. Proc. Jpn. Congr. Mater. Res. vol. 33, p. 177-9. 1990.

Affinito, J.D. et al., "PML/Oxide/PML Barrier Layer Performance Differences Arising From Use of UV or Electron Beam Polymerization of the PML Layers," Thin Solid Films. Elsevier Science S.A., vol. 308-309. Oct. 31, 1997. pp. 19-25.

Gustafsson, G. et al., "Flexible light-emitting diodes made from soluble conducting polymers." Nature. vol. 357, Jun. 11, 1992. pp. 447-479.

Affinito, J.D. et al., "Polymer-Oxide Transparent Barrier Layers." SVC 39th Annual Technical Conference. Vacuum Web Coating Session. 1996. pp. 392-397.

Affinito, J.D. et al., "PML/Oxide/PML Barrier Layer Performance Differences Arising From Use of UV or Electron Beam Polymerization of the PML Layers," SVC 40th Annual Technical Conference, 1997. pp. 19-25.

Wong, C.P., "Recent Advances in IC Passivation and Encapsulation: Process Techniques and Materials," Polymers for Electronic and Photonic Applications. AT&T Bell Laboratories. 1993. pp. 167-209.

De Geysl R. et al., Sputtered Transparent Barrier Layers. pp. 190-198, no date available.

Tropsha et al., "Activated Rate Theory Treatment of Oxygen and Water Transport through Silicon Oxide/Poly(ethylene terephthalate) Composite Barrier Structures," J. Phys. Chem B 199, pp. 2259-2266.

Tropsha et al., "Combinatorial Barrier Effect of the Multi-layer SiO₂ coatings on Polymer Substrates." 1997 Society of Vacuum Coaters, 40th Annual Technical Conference Proceedings, no page numbers.

Phillips et al., "Evaporated Dielectric Colorless Films on PET and OPP Exhibiting High Barriers Toward Moisture and Oxygen," Society of Vacuum Coaters. 36th Annual Technical Conference Proceedings (1993), pp. 293-300.

Chahroudi, "Transparent Glass Barrier Coatings for Flexible Film Packaging," Society of Vacuum Coaters, 34th Annual Technical Conference Proceedings (1991). pp. 130-133.

Yamada et al., "The Properties of a New Transparent and Colorless Barrier Film," Society of Vacuum Coaters, 38th Annual Technical Conference Proceedings (1995). pp. 28-31.

Affinito, J.D. et al., "Molecularly Doped Polymer Composite Films for Light Emitting Polymer Applications Fabricated by the PML Process" 1998 Society of Vacuum Coaters, 41st Annual Technical Conference Proceedings (1998). pp. 220-225.

Shi, M.K., et al., Plasma treatment of PET and acrylic coating surfaces-I. In situ XPS measurements, Journal of Adhesion Science and Technology. Mar. 2000, 14(12), pp. 1-28.

Shi, M.K., et al., In situ and real-time monitoring of plasma-induced etching PET and acrylic films. Plasmas and Polymers, Dec. 1999, 4(4), pp. 1-25.

Affinito, J.D., et al., Vacuum Deposited Conductive Polymer Films, The Eleventh International Conference on Vacuum Web Coating, earlier than Feb. 1998, pp. 200-213.

Mahon, J.K., et al., Requirements of Flexible Substrates for Organic Light Emitting Devices in Flat Panel Display Applications, Society of Vacuum Coaters. 42nd Annual Technical Conference Proceedings. Oct. 1999, pp. 456-459.

* cited by examiner




Fig. 1a (PRIOR ART)




Fig. 1b (PRIOR ART)




Fig. 2a (PRIOR ART)




Fig. 2b




Fig. 3




Fig. 3a




Fig. 4




Fig. 5a




Fig. 5b




Fig. 5c

METHOD OF MAKING A COATING OF A MICROTEXTURED SURFACE

This application is a continuation in part of application Ser. No. 09/212,780, filed Dec. 16, 1998, entitled "Conformal Coating of a Microtextured Surface", now U.S. Pat. No. 6,228,434.

FIELD OF THE INVENTION

The present invention relates generally to a method of making plasma polymerized polymer films. More specifically, the present invention relates to making a plasma polymerized polymer film onto a microtextured surface via plasma enhanced chemical deposition with a flash evaporated feed source of a low vapor pressure compound.

As used herein, the term "(meth)acrylic" is defined as "acrylic or methacrylic." Also, (meth)acrylate is defined as "acrylate or methacrylate."

As used herein, the term "cryocondense" and forms thereof refer to the physical phenomenon of a phase change from a gas phase to a liquid phase upon the gas contacting a surface having a temperature lower than a dew point of the gas.

As used herein, the term "polymer precursor" includes monomers, oligomers, and resins, and combinations thereof. As used herein, the term "monomer" is defined as a molecule of simple structure and low molecular weight that is capable of combining with a number of like or unlike molecules to form a polymer. Examples include, but are not limited to, simple acrylate molecules, for example, hexanedioldiacrylate, or tetraethyleneglycoldiacrylate, styrene, methyl styrene, and combinations thereof. The molecular weight of monomers is generally less than 1000, while for fluorinated monomers, it is generally less than 2000. Substructures such as CH₃, t-butyl, and CN can also be included. Monomers may be combined to form oligomers and resins, but do not combine to form other monomers.

As used herein, the term "oligomer" is defined as a compound molecule of at least two monomers that can be cured by radiation, such as ultraviolet, electron beam, or x-ray, glow discharge ionization, and spontaneous thermally induced curing. Oligomers include low molecular weight resins. Low molecular weight is defined herein as about 1000 to about 20,000 exclusive of fluorinated monomers. Oligomers are usually liquid or easily liquifiable. Oligomers do not combine to form monomers.

As used herein, the term "resin" is defined as a compound having a higher molecular weight (generally greater than 20,000) which is generally solid with no definite melting point. Examples include, but are not limited to, polystyrene resin, epoxy polyamine resin, phenolic resin, and acrylic resin (for example, polymethylmethacrylate), and combinations thereof.

BACKGROUND OF THE INVENTION

The basic process of plasma enhanced chemical vapor deposition (PECVD) is described in THIN FILM PROCESSES, J. L. Vossen, W. Kern, editors, Academic Press, 1978, Part IV, Chapter IV-1 Plasma Deposition of Inorganic Compounds, Chapter IV-2 Glow Discharge Polymerization, herein incorporated by reference. Briefly, a glow discharge plasma is generated on an electrode that may be smooth or have pointed projections. Traditionally, a gas inlet introduces high vapor pressure monomeric gases into the plasma region wherein radicals are formed so that upon subsequent collisions with the substrate, some of the radicals in the monomers chemically bond or cross link (cure) on the substrate. The high vapor pressure monomeric gases include

gases of CH₄, SiH₄, C₂H₆, C₂H₂, or gases generated from high vapor pressure liquid, for example styrene (10 torr at 87.4° F. (30.8° C.)), hexane (100 torr at 60.4° F. (15.8° C.)), tetramethyldisiloxane (10 torr at 82.9° F. (28.3° C.)), 1,3-dichlorotetramethyldisiloxane (75 torr at 44.6° F. (7.0° C.)), and combinations thereof that may be evaporated with mild controlled heating. Because these high vapor pressure monomeric gases do not readily cryocondense at ambient or elevated temperatures, deposition rates are low (a few tenths of micrometer/min maximum) relying on radicals chemically bonding to the surface of interest instead of cryocondensation. Remission due to etching of the surface of interest by the plasma competes with reactive deposition. Lower vapor pressure species have not been used in PECVD because heating the higher molecular weight monomers to a temperature sufficient to vaporize them generally causes a reaction prior to vaporization, or metering of the gas becomes difficult to control, either of which is inoperative.

The basic process of flash evaporation is described in U.S. Pat. No. 4,954,371 herein incorporated by reference. This basic process may also be referred to as polymer multi-layer (PML) flash evaporation. Briefly, a radiation polymerizable and/or cross linkable material is supplied at a temperature below a decomposition temperature and polymerization temperature of the material. The material is atomized to droplets having a droplet size ranging from about 1 to about 50 microns. An ultrasonic atomizer is generally used. The droplets are then flash vaporized, under vacuum, by contact with a heated surface above the boiling point of the material, but below the temperature which would cause pyrolysis. The vapor is cryocondensed on a substrate then radiation polymerized or cross linked as a very thin polymer layer.

According to the state of the art of making plasma polymerized films, PECVD and flash evaporation or glow discharge plasma deposition and flash evaporation have not been used in combination. However, plasma treatment of a substrate using a glow discharge plasma generator with inorganic compounds has been used in combination with flash evaporation under a low pressure (vacuum) atmosphere, as reported in J. D. Affinito, M. E. Gross, C. A., Coronado, and P. M. Martin, "Vacuum Deposition Of Polymer Electrolytes On Flexible Substrates," Proceedings of the Ninth International Conference on Vacuum Web Coating, November 1995, ed. R. Bakish, Bakish Press 1995, pg. 20-36, and as shown in FIG. 1a. In that system, the plasma generator **100** is used to etch the surface **102** of a moving substrate **104** in preparation to receive the monomeric gaseous output from the flash evaporation **106** that cryocondenses on the etched surface **102** and is then passed by a first curing station (not shown), for example electron beam or ultra-violet radiation, to initiate cross linking and curing. The plasma generator **100** has a housing **108** with a gas inlet **110**. The gas may be oxygen, nitrogen, water or an inert gas, for example argon, or combinations thereof. Internally, an electrode **112** that is smooth or having one or more pointed projections **114** produces a glow discharge and makes a plasma with the gas which etches the surface **102**. The flash evaporator **106** has a housing **116**, with a monomer inlet **118** and an atomizing nozzle **120**, for example an ultrasonic atomizer. Flow through the nozzle **120** is atomized into particles or droplets **122** which strike the heated surface **124** whereupon the particles or droplets **122** are flash evaporated into a gas that flows past a series of baffles **126** (optional) to an outlet **128** and cryocondenses on the surface **102**. Although other gas flow distribution arrangements have been used, it has been found that the baffles **126** provide adequate gas flow distribution or uniformity while permitting ease of scaling up to large surfaces **102**. A curing station (not shown) is located downstream of the flash evaporator **106**. The monomer may be an acrylate (FIG. 1b).

These flash evaporation methods have traditionally been used on smooth surfaces or surfaces lacking microtextured

3

features. A disadvantage of traditional PML (polymer multi-layer) flash evaporation methods is that during the time between condensation of the vapor to a liquid film and the radiation cross linking of the liquid film to a solid layer, the liquid tends to flow preferentially to low points and flatter regions because of gravity and surface tension (FIG. 2a) so that the coating surface 150 is geometrically different from the substrate surface 160. Reducing surface temperature can reduce the flow somewhat, but should the monomer freeze, then cross linking is adversely affected. Using higher viscosity monomers is unattractive because of the increased difficulty of degassing, stirring, and dispensing of the monomer.

Many devices have microtextured surfaces, for example, quasi-comer reflector type micro-retroreflectors, diffraction gratings, micro light pipes and/or wave guides, and micro-channel flow circuits. The devices are presently made by spin coating or physical vapor deposition (PVD). Physical vapor deposition may be either evaporation or sputtering. With spin coating, surface area coverage is limited and scaling up to large surface areas requires multiple parallel units rather than a larger single unit. Moreover, physical vapor deposition processes are susceptible to pin holes.

Therefore, there is a need for coating devices that have microtextured surfaces with a conformal coating.

SUMMARY OF THE INVENTION

The present invention is a method of conformally coating a microtextured surface. The method includes plasma polymerization wherein a polymer precursor is cured during plasma polymerization. The method is a combination of flash evaporation with plasma enhanced chemical vapor deposition (PECVD) that provides the unexpected improvements of conformally coating a microtextured substrate at a rate surprisingly faster than standard PECVD deposition rates.

The conformal coating material may be a polymer precursor, or a mixture of polymer precursor with particle materials. The polymer precursor, particle, or both may be conjugated, or unconjugated.

The method of the present invention includes flash evaporating a polymer precursor forming an evaporate, passing the evaporate to a glow discharge electrode creating a glow discharge polymer precursor plasma from the evaporate, and cryocondensing the glow discharge polymer precursor plasma on a microtextured surface as a condensate, and polymerizing the condensate before the condensate flows, thereby conformally coating the microtextured surface. The crosslinking results from radicals created in the glow discharge plasma.

Accordingly, the present invention provides a method of conformally coating a microtextured surface.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1a is a cross section of a prior art combination of a glow discharge plasma generator with inorganic compounds with flash evaporation.

FIG. 1b is a chemical diagram of a (meth-)acrylate molecule.

FIG. 2a is an illustration of a non-conformal coating (prior art).

FIG. 2b is an illustration of a conformal coating according to the method of the present invention.

FIG. 3 is a cross section of an apparatus which can be used in method of the present invention of combined flash evaporation and glow discharge plasma deposition.

FIG. 3a is a cross section end view of the apparatus of FIG. 3.

4

FIG. 4 is a cross section of an apparatus wherein the substrate is the electrode.

FIG. 5a is a chemical diagram including phenylacetylene.

FIG. 5b is a chemical diagram of triphenyl diamine derivative.

FIG. 5c is a chemical diagram of quinacridone.

DETAILED DESCRIPTION OF THE INVENTION

The present invention is a method of conformally coating a microtextured surface. Microtextured surfaces include but are not limited to quasi-comer reflector type micro-retroreflectors, diffraction gratings, microlight pipes and/or wave guides, microchannel flow circuits and combinations thereof. A conformal coating is illustrated in FIG. 2b wherein a coating surface 150 is geometrically similar to the microtextured surface 160. Conformally coating a microtextured surface may be done with the apparatus shown in FIG. 3. The method of the present invention may be performed within a low pressure (vacuum) environment or chamber. Pressures typically range from about 10^{-1} torr to 10^{-6} torr, although they may be higher or lower. The flash evaporator 106 has a housing 116, with a polymer precursor inlet 118 and an atomizing nozzle 120. Flow through the nozzle 120 is atomized into particles or droplets 122 which strike the heated surface 124 whereupon the particles or droplets 122 are flash evaporated into a gas or evaporate that flows past a series of baffles 126 to an evaporate outlet 128 and cryocondenses on the microtextured surface 102. Cryocondensation on the baffles 126 and other internal surfaces is prevented by heating the baffles 126 and other surfaces to a temperature in excess of a cryocondensation temperature or dew point of the evaporate. Although other gas flow distribution arrangements have been used, it has been found that the baffles 126 provide adequate gas flow distribution or uniformity while permitting ease of scaling up to large microtextured surfaces 102. The evaporate outlet 128 directs gas toward a glow discharge electrode 204 creating a glow discharge plasma from the evaporate. In the embodiment shown in FIG. 3, the glow discharge electrode 204 is placed in a glow discharge housing 200 having an evaporate inlet 202 proximate the evaporate outlet 128. In this embodiment, the glow discharge housing 200 and the glow discharge electrode 204 are maintained at a temperature above a dew point of the evaporate. The glow discharge plasma exits the glow discharge housing 200 and cryocondenses on the microtextured surface 102 of the microtextured substrate 104. It is preferred that the microtextured substrate 104 is kept at a temperature below a dew point of the evaporate, preferably ambient temperature or cooled below ambient temperature to enhance the cryocondensation rate. In this embodiment, the microtextured substrate 104 is moving and may be electrically grounded, electrically floating, or electrically biased with an impressed voltage to draw charged species from the glow discharge plasma. If the microtextured substrate 104 is electrically biased, it may even replace the electrode 204 and be, itself, the electrode which creates the glow discharge plasma from the polymer precursor gas. Electrically floating means that there is no impressed voltage although a charge may build up due to static electricity or due to interaction with the plasma.

A preferred shape of the glow discharge electrode 204, is shown in FIG. 3a. In this embodiment, the glow discharge electrode 204 is separate from the microtextured substrate 104 and is shaped so that evaporate flow from the evaporate inlet 202 substantially flows through an electrode opening 206. Any electrode shape can be used to create the glow discharge, however, the preferred shape of the electrode 204 does not shadow the plasma from the evaporate issuing from

5

the outlet **202** and its symmetry, relative to the polymer precursor exit slit **202** and microtextured substrate **104**, provides uniformity of the evaporate vapor flow to the plasma across the width of the substrate while uniformity transverse to the width follows from the substrate motion.

The spacing of the electrode **204** from the microtextured substrate **104** is a gap or distance that permits the plasma to impinge upon the substrate. This distance that the plasma extends from the electrode will depend on the evaporate species, electrode **204**/microtextured substrate **104** geometry, electrical voltage and frequency, and pressure in the standard way as described in detail in *ELECTRICAL DISCHARGES IN GASSES*, F. M. Penning, Gordon and Breach Science Publishers, 1965, and summarized in *THIN FILM PROCESSES*, J. L. Vossen, W. Kern, editors, Academic Press, 1978, Part II, Chapter II-1, Glow Discharge Sputter Deposition, both hereby incorporated by reference.

An apparatus suitable for batch operation is shown in FIG. 4. In this embodiment, the glow discharge electrode **204** is sufficiently proximate a part **300** (microtextured substrate) that the part **300** is an extension of or part of the electrode **204**. Moreover, the part is below a dew point to allow cryocondensation of the glow discharge plasma on the part **300** and thereby coat the part **300** with the polymer precursor condensate and self cure into a polymer layer. Sufficiently proximate may be connected to, resting upon, in direct contact with, or separated by a gap or distance that permits the plasma to impinge upon the substrate. This distance that the plasma extends from the electrode will depend on the evaporate species, electrode **204** microtextured substrate **104** geometry, electrical voltage and frequency, and pressure in the standard way as described in *ELECTRICAL DISCHARGES IN GASSES*, F. M. Penning, Gordon and Breach Science Publishers, 1965, hereby incorporated by reference. The substrate **300** may be stationary or moving during cryocondensation. Moving includes rotation and translation and may be employed for controlling the thickness and uniformity of the polymer precursor layer cryocondensed thereon. Because the cryocondensation occurs rapidly, within milli-seconds to seconds, the part may be removed after coating and before it exceeds a coating temperature limit.

In operation, either as a method for plasma enhanced chemical vapor deposition of low vapor pressure materials (coating material) onto a microtextured surface, or as a method for making self-curing polymer layers (especially PML), the method of the invention includes flash evaporating a polymer precursor forming an evaporate, passing the evaporate to a glow discharge electrode creating a glow discharge polymer precursor plasma from the evaporate, and

6


cryocondensing the glow discharge polymer precursor plasma on a substrate as a condensate and crosslinking the condensate thereon, the crosslinking resulting from radicals created in the glow discharge plasma.

The flash evaporating may be performed by supplying a continuous liquid flow of the polymer precursor into a vacuum environment at a temperature below both the decomposition temperature and the polymerization temperature of the polymer precursor, continuously atomizing the polymer precursor into a continuous flow of droplets, and continuously vaporizing the droplets by continuously contacting the droplets on a heated surface having a temperature at or above a boiling point of the liquid polymer precursor, but below a pyrolysis temperature, forming the evaporate. The droplets typically range in size from about 1 micrometer to about 50 micrometers, but they could be smaller or larger.

Alternatively, the flash evaporating may be performed by supplying a continuous liquid flow of the polymer precursor into a vacuum environment at a temperature below both the decomposition temperature and the polymerization temperature of the polymer precursor, and continuously directly vaporizing the liquid flow of the polymer precursor by continuously contacting the liquid polymer precursor on a heated surface having a temperature at or above the boiling point of the liquid polymer precursor, but below the pyrolysis temperature, forming the evaporate. This maybe done using the vaporizer disclosed in U.S. Pat. Nos. 5,402,314, 5,536,323, and 5,711,816, which are incorporated herein by reference.

The polymer precursor may be any liquid polymer precursor. However, it is preferred that the liquid polymer precursor has a low vapor pressure at ambient temperatures so that it will readily cryocondense. The vapor pressure of the liquid polymer precursor may be less than about at 10 torr at 83° F. (28.3° C.), less than about 1 torr at 83° F. (28.3° C.), and less than about 10 millitorr at 83° F. (28.3° C.). Liquid polymer precursors include, but are not limited to, phenylacetylene (FIG. 5a), (meth)acrylates, alkenes, and alkynes, and combinations thereof.

Further, to increase its functionality the liquid polymer precursor may include additional materials which may be soluble, insoluble, or partially soluble in the liquid polymer precursor. The particle(s) may be any soluble, insoluble, or partially soluble particle type having a boiling point below a temperature of the heated surface in the flash evaporation process. Soluble particles include, but are not limited to, substituted metal tris (N—R 8-quinolinolato) chelates, wherein N is between 2 and 7 and is the substituent position of the ligand, and wherein R is H, alkyl, alkoxy, and fluorinated hydrocarbons; and substituted tertiary aromatic amines; such as for example:





$n = 3, M = Al^{+3}, Ga^{+3}, In^{+3}$

$n = 1, M = Li^{+1}$


R = alkyl, alkoxy, and fluorinated hydrocarbons

7



R = H, alkyl, alkoxy,
and fluorinated hydrocarbons

-continued



M = Al⁺³, Ga⁺³, In⁺³
R = alkyl, alkoxy, and fluorinated
hydrocarbons
L = monodentate ligand, such as
carboxylate, phenolate and derivatives of.

8

Insoluble particles include, but are not limited to, tertiary aromatic amines such as, triphenyl diamine derivatives (TPD, FIG. 5b), quinacridone derivatives (QA, FIG. 5c), and metal (8-quinolinolato) chelates, such as aluminum quinolinolato, (Alq), gallium quinolinolato (Gaq), and lithium quinolinolato (Liq), and combinations thereof. Partially soluble means that some of the particles do not dissolve in the polymer precursor, including the situation in which a soluble particle is present in a concentration exceeding the solubility limit in the polymer precursor so that some of the dissolvable material remains undissolved.

The particles generally have a volume much less than about 5000 cubic micrometers (diameter about 21 micrometers) or equal thereto, typically less than or equal to about 4 cubic micrometers (diameter about 2 micrometers). The insoluble particles may be sufficiently small with respect to particle density and liquid polymer precursor density and viscosity that the settling rate of the particles within the liquid polymer precursor is several times greater than the amount of time to transport a portion of the particle liquid polymer precursor mixture from a reservoir to the atomization nozzle. It may be necessary to agitate the particle liquid polymer precursor mixture in the reservoir to maintain suspension of the particles and avoid settling. As used herein, agitation includes, but is not limited to, stirring, physical shaking, ultrasonic vibration, and convection (thermal gradient).

The mixture of polymer precursor and soluble, insoluble, or partially soluble particles may be considered a solution, slurry, suspension or emulsion, and the particles may be solid or liquid. The mixture may be obtained by several methods. One method is to mix insoluble particles of a specified size into the polymer precursor. The insoluble particles of a solid of a specified size may be obtained by direct purchase or by making them by one of any standard techniques, including, but not limited to, milling from large particles, precipitation from solution, melting/spraying under controlled atmospheres, rapid thermal decomposition of precursors from solution as described in U.S. Pat. No. 5,652,192 hereby incorporated by reference. The steps of

U.S. Pat. No. 5,652,192 are making a solution of a soluble precursor in a solvent and flowing the solution through a reaction vessel, pressurizing and heating the flowing solution and forming substantially insoluble particles, then quenching the heated flowing solution and arresting growth of the particles. Alternatively, larger sizes of solid material may be mixed into liquid polymer precursor then agitated, for example ultrasonically, to break the solid material into particles of sufficient size.

Liquid particles may be obtained by mixing an immiscible liquid with the polymer precursor liquid and agitating by ultrasonic or mechanical mixing to produce liquid particles within the liquid polymer precursor. Immiscible liquids include, for example, phenylacetylene.

If an atomizer is used, upon spraying, the droplets may be particles alone, particles surrounded by liquid polymer precursor, and liquid polymer precursor alone. Since both the liquid polymer precursor and the particles are evaporated, it is of no consequence either way. The droplets should be sufficiently small that they are completely vaporized. The droplet size typically ranges from about 1 micrometer to about 50 micrometers, although the particles may be larger or smaller.

By using flash evaporation, the coating material polymer precursor is vaporized so quickly that reactions that generally occur from heating a liquid material to an evaporation temperature simply do not occur. Further, control of the rate of evaporate delivery is strictly controlled by the rate of material delivery to the inlet **118** of the flash evaporator **106**.

In addition to the evaporate from the polymer precursor, additional gases may be added within the flash evaporator **106** through a gas inlet **130** upstream of the evaporate outlet **128**, preferably between the heated surface **124** and the first baffle **126** nearest the heated surface **124**. Additional gases may be organic or inorganic for purposes including, but not limited to, ballast, reaction, and combinations thereof. Ballast refers to providing sufficient molecules to keep the plasma lit in circumstances of low evaporate flow rate. Reaction refers to chemical reaction to form a compound different from the evaporate. Additional gases include but

are not limited to group VIII of the periodic table, hydrogen, oxygen, nitrogen, chlorine, bromine, polyatomic gases including for example carbon dioxide, carbon monoxide, water vapor, and combinations thereof.

The method of the present invention is insensitive to a direction of motion of the substrate because the deposited polymer precursor layer is self curing. Also, the conjugation (if any) is preserved during curing. In addition, multiple layers of materials may be combined. For example, as recited in U.S. Pat. Nos. 5,547,508 and 5,395,644, 5,260,095, hereby incorporated by reference, multiple polymer layers, alternating layers of polymer and metal, and other layers may be made with the present invention in the vacuum environment.

While a preferred embodiment of the present invention has been shown and described, it will be apparent to those skilled in the art that many changes and modifications may be made without departing from the invention in its broader aspects. The appended claims are therefore intended to cover all such changes and modifications as fall within the true spirit and scope of the invention.

We claim:

1. A method of conformally coating a microtextured surface, comprising:

(a) making an evaporate by receiving a polymer precursor into a flash evaporation housing, evaporating the polymer precursor on an evaporation surface, and discharging the evaporate through an evaporate outlet;

(b) making a polymer precursor plasma from the evaporate by passing the evaporate proximate a glow discharge electrode; and

(c) cryocondensing the polymer precursor plasma as a condensate onto the microtextured surface and polymerizing the condensate before the condensate flows thereby conformally coating the microtextured surface.

2. The method as recited in claim 1, wherein the microtextured surface is proximate the glow discharge electrode, and is electrically biased with an impressed voltage.

3. The method as recited in claim 1, wherein the glow discharge electrode is positioned within a glow discharge housing having an evaporate inlet proximate the evaporate outlet, the glow discharge housing and the glow discharge electrode maintained at a temperature above a dew point of the evaporate, and the microtextured surface is downstream of the polymer precursor plasma, and is electrically floating.

4. The method as recited in claim 1, wherein the microtextured surface is proximate the glow discharge electrode, and is electrically grounded.

5. The method as recited in claim 1, wherein the polymer precursor is selected from the group of phenylacetylene, (meth)acrylates, alkenes, and alkynes, and combinations thereof.

6. The method as recited in claim 1, wherein the microtextured surface is cooled.

7. The method as recited in claim 1, further comprising adding an additional gas to the evaporate.

8. The method as recited in claim 7, wherein the additional gas is a ballast gas.

9. The method as recited in claim 7, wherein the additional gas is a reaction gas.

10. A method for conformally coating a microtextured surface in a vacuum chamber, comprising:

(a) flash evaporating a polymer precursor forming an evaporate;

(b) passing the evaporate to a glow discharge electrode creating a glow discharge polymer precursor plasma from the evaporate; and

(c) cryocondensing the glow discharge polymer precursor plasma as a condensate on the microtextured surface and crosslinking the condensate thereon, the crosslinking resulting from radicals created in the glow discharge polymer precursor plasma for self curing, the crosslinking occurring before the condensate flows, thereby conformally coating the microtextured surface.

11. The method as recited in claim 10, wherein the microtextured surface is proximate the glow discharge electrode, and is electrically biased with an impressed voltage.

12. The method as recited in claim 10, wherein the glow discharge electrode is positioned within a glow discharge housing having an evaporate inlet proximate the evaporate outlet, the glow discharge housing and the glow discharge electrode maintained at a temperature above a dew point of the evaporate, the microtextured surface is downstream of the glow discharge polymer precursor plasma, and is electrically floating.

13. The method as recited in claim 10, wherein the microtextured surface is proximate the glow discharge electrode, and is electrically grounded.

14. The method as recited in claim 10, wherein the polymer precursor is selected from the group of phenylacetylene, (meth)acrylates, alkenes, and alkynes, and combinations thereof.

15. The method as recited in claim 10, wherein the microtextured surface is cooled.

16. The method as recited in claim 10, further comprising adding an additional gas to the evaporate.

17. The method as recited in claim 16, wherein the additional gas is a ballast gas.

18. The method as recited in claim 16, wherein the additional gas is a reaction gas.

19. The method as recited in claim 10, wherein flash evaporating comprises:

(a) supplying a continuous liquid flow of the polymer precursor into a vacuum environment at a temperature below both the decomposition temperature and the polymerization temperature of the polymer precursor;

(b) continuously atomizing the polymer precursor into a continuous flow of droplets; and

(c) continuously vaporizing the droplets by continuously contacting the droplets on a heated surface having a temperature at or above a boiling point of the polymer precursor, but below a pyrolysis temperature, forming the evaporate.

20. The method as recited in claim 19 wherein the droplets range in size from about 1 micrometer to about 50 micrometers.

21. The method as recited in claim 10 wherein flash evaporating comprises:

(a) supplying a continuous liquid flow of the polymer precursor into a vacuum environment at a temperature below both the decomposition temperature and the polymerization temperature of the polymer precursor; and

(b) continuously directly vaporizing the liquid flow of the polymer precursor by continuously contacting the polymer precursor on a heated surface having a temperature at or above a boiling point of the polymer precursor, but below a pyrolysis temperature, forming the evaporate.